

# Series 29 Architectural Application

A POWDER COATING FOR METAL FACADES AND STEEL CONSTRUCTION  
BASIS: ON POLYESTER

## Typical application

- metal facades
- steel construction
- traffic signals

## Product details

**Standard Packaging** In original boxes of 20 kg each as well as in Minipacks of 2.5 kg each

**Specific Gravity (ISO 8130-2)** 1.2-1.7 g/cm<sup>3</sup> depending on pigmentation

**Theoretical Coverage** at 60 µm film thickness: 9.8-13.8 m<sup>2</sup>/kg depending on specific gravity (please see also Information Sheet no. 1072 - latest edition)

**Storage Stability** Use before: see printed date on product label; under dry conditions at no more than 25 °C, avoid direct and extended heat exposure

(The shelf life of custom made blanket orders or other stock agreements which by their nature are stored over longer periods is determined by the original production date.)

## Features

- highly weather resistant
- very good flow properties
- very good mechanical properties
- good storage stability
- batch consistency of RAL colors acc. to VdL guidance no. 10

## Finish

Finish	Gloss
smooth <i>glossy</i>	80 – 95*
smooth <i>semi gloss</i>	65 – 75*
smooth <i>matte</i>	20 – 30*
fine texture <i>matte</i>	-
rough texture <i>glossy</i>	-

\* Gloss level acc. to ISO 2813/60° angle (doesn't apply to metallic effect powder coatings). The measured gloss level of effect powder coatings can diverge from the details given in this product datasheet. The creation of tolerance samples is urgently recommended)

## Pre-treatments

The following table reflects the common methods of pretreatment with regards to various substrates and applications. In selecting the proper type of pretreatment please observe the suitability of the type of powder coating for a desired application according to the guidelines of this Product Data Sheet.

	Alu- minum			Galvanized Steel			Steel		
Degreasing	○			○			○		
<sup>1)</sup> Chromating	○	○	○	○	○	○	○	○	○
<sup>2)</sup> Pre-Anodizing	○	○	○						
<sup>2)</sup> Chrome free	○	○	○	○	○				
Iron Phosphating							○		
Zinc Phosphating				○	○	○	○	○	○
Blasting							○	○	○
<sup>3)</sup> Sweeping				○	○	○	○	○	○
	I	E	A	I	E	A	S	I	S <sup>4)</sup>

Application: I = interior; E = exterior; A = architectural; S = steel

- 1) acc. to DIN 50939
- 2) acc. to GSB quality and test regulations. The suitability of this type of pretreatment needs to be established through a boiling water test and subsequent cross-hatch adhesion and adhesive tape removal test.
- 3) only for zinc coated parts > 45 µm
- 4) for a two-coat process TIGER Shield

## Processing

### Corona, Tribostatic\*

\* Suitability of metallic and fine texture effects for tribo processing must be verified prior to actual application. Please consult with the relevant application guidelines for metallic effect powder coatings, latest edition.

## Material approvals for colors and metallic effects\*

Quality labels for the piecework coating of building components

Finish	GSB Standard	QUALICOAT Class 1	AAMA 2603
smooth <i>glossy</i>	107m	P-0909	-
smooth <i>semi gloss</i>	107q	P-0266	✓
smooth <i>matte</i>	107i	P-0267	✓
fine texture <i>matte</i>	174b	P-0630	-
rough texture <i>glossy</i>	-	-	-

\* exemptions prevail




## Cure parameters

(Substrate temperature versus curing time)

smooth *glossy* | rough texture *glossy*

smooth *semi gloss*

smooth *matte* | fine texture *matte*



Please observe cure parameters closely since mechanical properties will develop before full cross-linking!

## Test results

Checked under laboratory conditions on a chromated aluminum test panel which is 0.7 mm thick. Actual product performance may vary due to product specific properties such as gloss, color, effect and finish as well as application related and environmental influences.

test method	test	Series 29 smooth <i>glossy</i>   smooth <i>semigloss</i>   smooth <i>matte</i>	Series 29 fine texture <i>matte</i>	Series 29 rough texture <i>glossy</i>
ISO 2360	<b>film thickness recommended</b>	60-80 µm	70-90 µm	90-120 µm
ISO 2813	<b>gloss - 60°</b>	gl. 80-95   sgl. 65-75   <i>matte</i> 20-30	visual <i>matte</i>	visual <i>glossy</i>
ISO 2409	<b>cross cut test/adhesion</b> 1 mm cutting distance	0	0	0
ISO 1519	<b>mandrel bending test</b> cracking of coating	≤ 5 mm not permitted	≤ 5 mm not permitted	≤ 10 mm not permitted
ISO 2815	<b>impression hardness</b>	≥ 80	not measurable	not measurable
ISO 1520	<b>cupping test</b> cracking of coating	≥ 5 mm not permitted	≥ 5 mm not permitted	≥ 5 mm not permitted
ASTM D 2794	<b>ball impact test</b> cracking of coating	20 Inch/pound not permitted	20 Inch/pound not permitted	20 inch/pound not permitted
ISO 6270-1	<b>determination of resistance to humidity</b> 1000 h	infiltration at cross-section max. blistering 1 mm	infiltration at cross-section max. blistering 1 mm	infiltration at cross-section max. blistering 1 mm
ISO 9227	<b>salt spray test</b> 1000 h	infiltration at cross-section max. blistering 1 mm	infiltration at cross-section max. blistering 1 mm	infiltration at cross-section max. blistering 1 mm
acc. to EN ISO 16474-3	<b>accelerated weathering</b> UV-B (313 nm) 300 h *	residual gloss ≥ 50 %	residual gloss ≥ 50 %	residual gloss ≥ 50 %
EN ISO 16474-2	<b>accelerated weathering test</b> xenon-arc radiation 1000 h **	residual gloss ≥ 50 %	residual gloss ≥ 50 %	residual gloss ≥ 50 %
EN ISO 2810	<b>natural weathering</b> in Florida 12 month	residual gloss ≥ 50 %	residual gloss ≥ 50 %	residual gloss ≥ 50 %

\* acc. to GSB AL 631 ([www.gsb-international.de](http://www.gsb-international.de)) \*\* acc. to QUALICOAT specifications ([www.qualicoat.net](http://www.qualicoat.net))

## Processing instructions

The guidelines for application (datasheet 1213) must be strictly observed.

The Product Data Sheets, Technical Information Sheets and the guidelines for application each in their latest version, available as a download at [www.tiger-coatings.com](http://www.tiger-coatings.com).

## Disclaimer

Our verbal and written recommendations for the use of our products are based upon experience and in accordance with present technological standards. These are given in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of our products for the intended application. We warrant that our products are free of flaws and defects to the extent as stipulated in our Terms of Delivery and Payment.

As a part of our product information program each of our Product Data Sheets are periodically updated, so that the latest version shall prevail. Therefore, please visit the download area of [www.tiger-coatings.com](http://www.tiger-coatings.com) to make sure you have the most current version of this Product Data Sheet. The information in our Product Data Sheets is subject to change without notification.

**This Product Data Sheet substitutes any and all previous Product Data Sheets and notes for customers published on this subject matter and is only intended to give a general product overview. Please request specific information for products outside of our standard product list (latest version).**

**The Technical Information Sheets and the Terms of Delivery and Payment each in their latest version, available as a download at [www.tiger-coatings.com](http://www.tiger-coatings.com), form an integral part of this Product Data Sheet.**

certified according to  
EN ISO 9001 / 14001



### TIGER Coatings GmbH & Co. KG

Negrellistrasse 36 | 4600 Wels | Austria

T +43 / (0)7242 / 400-0

F +43 / (0)7242 / 650 08

E [powdercoatings@tiger-coatings.com](mailto:powdercoatings@tiger-coatings.com)

W [www.tiger-coatings.com](http://www.tiger-coatings.com)